







Meactive® SEL (Super Exhaust & Levelling) Dyes			1/1 Standard Depth %	Process Suitability						Light Source ISO 105 B02		Washing ISO3	Perspiration ISO 105 E04				Rubbing Fastness ISO 105 X12		Chlorinated Water ISO 105 E02	Dischargeability	
				Warm Exhaust	Cold Pad Batch	Pad Dry Pad Steam	Pad Dry Steam	Econtrol	Solubility (g/l) 30°C	1/6 1/1			Acidic		Alkaline		Dry	Wet			
E	S	E								S	Dry		Wet								
80°C	0.50%	3.00%																			
Yellow SEL			3.0	S	NS	NS	NS	NS	150	4-5	5	5	5	5	5	5	5	4-5	4	4	ND
Crimson SEL			2.0	S	NS	NS	NS	NS	150	3-4	4	5	4	4-5	4	4-5	4	4	3-4	4-5	ND
Navy SEL			2.8	S	NS	NS	NS	NS	150	3-4	4	5	4	4-5	4	5	4-5	3-4	3-4	3-4	ND

- Meactive® SEL dyes have excellent reproducibility and level dyeing in difficult dyeing conditions.
- Suitable for post mercerization with excellent leveling properties.
- Highly recommended for articles with poor dye penetration e.g.CV, merc.CO, CEL/elastomeric fibers, garment dyeing, articles with poor dye penetration.
- Suitable and robust for dyeing PES/CEL blends, Good oxidative wash fastness (multiple wash cycles).
- Compatible with Meactive® HE dyes.

S = Suitable  
NS = Not Suitable

LS = Less Suitable  
D = Dischargeable

ND = Not Dischargeable  
PD = Partially Dischargeable